

PRODUCT DATA SHEET



www.bestor.ee

Bestor Grupp AS
Valdeku 168, 11217, Tallinn, Estonia
+372 518 0889

Mineroll TOP 5000

Document number : BG1448

Publication Date: 11.01.2023 Revision date : 11.01.2023

| | | | | |
|---|--|-------------------|------------------|---------------|
| PRODUCT DESCRIPTION | Elastomeric modified bituminous waterproofing membrane | | | |
| USAGE | Used as top layer or single layer to waterproof terraces and roofs | | | |
| APPLICATION METHOD | Torched. Please refer to application booklet | | | |
| TOP SURFACE | Mineral | | | |
| BOTTOM SURFACE | Polyethylene Film | | | |
| REINFORCEMENT TYPE | Polyester | | | |
| STORAGE | Rolls to be stored upright and away from heat | | | |
| ECOLOGICAL DATA | Can be used in natural atmosphere | | | |
| TEST | METHOD | UNIT | TOLERANCE | VALUES |
| Visible defects | EN 1850-1 | - | - | NONE |
| Length | EN 1848-1 | m | -0,03 | 8 |
| Width | EN 1848-1 | m | -0,02 | 1 |
| Straightness | EN 1848-1 | - | - | PASS |
| Unit of weight | EN 1849-1 | kg/m ² | ±%10 | 5 |
| Watertightness | EN 1928 (method A 10kPa) | - | - | PASS |
| Reaction to fire | EN 13501-1 | class | - | E |
| External Fire Performance | ENV 1187 EN 13501-5 | class | - | Broof |
| Shear resistance of joint | EN 12317-1 | N/50mm | ±30% | 850 |
| Water vapour transmission properties | EN 1931 | - | min. | 20.000 |
| Tensile Strength (Longitudinal) | EN 12311-1 | N/50mm | -%10 ; +%40 | 800 |
| Elongation at break (Longitudinal) | EN 12311-1 | % | (-0 ; +20) | 35 |
| Tensile Strength (Transverse) | EN 12311-1 | N/50mm | -%10 ; +%40 | 600 |
| Elongation at break (Transverse) | EN 12311-1 | % | (-0 ; +20) | 35 |
| Resistance to impact | EN 12691 (method A) | mm | min. | 1500 |
| Resistance to static loading | EN 12730 (method B) | kg | min. | 20 |
| Resistance to tearing (Longitudinal) | EN 12310-1 | N | ±50% | 270 |
| Flexibility at low temperature | EN 1109 (top surface) | °C | min. | -20 |
| | EN 1109 (bottom surface) | °C | min. | -20 |
| | Artificial aging (EN 1296) | °C | (-0 ; +10) | -20 |
| Flow resistance at elevated temperature(<2mm) | EN 1110 | °C | min. | 100 |
| | Artificial aging (EN 1296) | °C | (-10 ; +0) | 100 |
| Dimensional stability | EN 1107-1 | % | max. | 0,6 |
| Adhesion of granules | EN 12039 | % | max. | 30 |
| Dangerous substances | Doesn't contain asbestos or coal tar constituents. | | | |

NPd = (No performance defined)

* For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data

THE manufacturer serves the right to modify, at any time, the characteristics of its products

BF/14-17-0